




BULLETBLOCK™
BULLET RESISTANT WINDOWS, DOORS & GLAZING
BY INSULGARD

ACRYSHIELD™ SMG 1.25 LEVEL 6 ACRYLIC



Innovative glazing solutions for ballistic protection

PRODUCT DESCRIPTION

ACRYSHIELD™ SMG 1.25 ACRYLIC HAS BEEN TESTED AND CERTIFIED TO MEET UL 752 LEVEL 6 BALLISTICS PERFORMANCE

TECHNICAL DATA

- Nominal Thickness: 1.25"
- Weight: 7.7 lbs per SF
- Light Transmittance: >85%
- Haze: <1.5%
- Yellowness Index: <1.0%
- Abrasion Resistance (coated): .2 to 2.0 (% haze change)
- Abrasion Resistance (uncoated): 14 (% haze change)
- Tensile Strength: 9,400psi
- Tensile Modulus: 400,000psi
- Flex Modulus: 400,000psi
- Burn Rate: .23in/min
- Smoke Density: Max 8%: Rating 5%
- Auto Ignition Temp: 465°C, 870°F

PERFORMANCE

- 5 shots 9mm Submachine Gun/Uzi
- UL 752 – Level 6
- No Spall, No Penetration

OPTIONS:

- Standard Tints
- Sheet sizes up to 6' x 10'

CODE RATINGS AND STANDARDS

- Meets the test requirements of Building Code class CC2
- ANS, Z97.1 - Safety Glazing Material
- ANS, Z26.1 - Motor Vehicle Safety Glazing Material
- Dade County Approval, Federal
- Specification L-P-391D+ASTM D 4802

Maximum Continuous Service Temperature:

170 degrees F

Minimum Continuous Service Temperature:

-26 degrees F (lowest temperature tested for bullet resistance)

Polycast and SAR are either registered trademarks or trademarks of Spartech Polycast.

The materials, products, and services of Insulgard™ Security Products, its subsidiaries and affiliates ("Seller") are sold subject to Seller's standard conditions of sale, which can be found at www.polymershapes.com and are available upon request. Although any information or recommendation contained herein is given in good faith, Seller makes no warranty or guarantee, express or implied, (i) that the results described herein will be obtained under end-use conditions, or (ii) as to the effectiveness or safety of any design incorporating seller's products, services or recommendations. Except as provided in Seller's standard conditions of sale, Seller shall not be responsible for any loss resulting from any use of its products or services described herein. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. No statement by Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right. ©2020 Polymershapes LLC. All rights reserved. BulletBlock™ and Insulgard™ are trademarks of Polymershapes LLC. Version: 7.27.20

INSULGARD™
SECURITY PRODUCTS
insulgard.com | 800.624.6315