




**FORCEPROTECT**  
FORCED ENTRY RESISTANT GLASS  
BY INSULGARD

## LEXGARD® MPC375



### TECHNICAL DATA

- Nominal Thickness: .369"
- Tolerance: .332" / .406"
- Weight: 2.29 lbs per SF
- Available Sizes: Up to 72" x 96"
- Light Transmittance: 77%
- U-Value: .84
- Shading Coefficient: .92
- Translucent white interlayer available

### PERFORMANCE

- Forced Entry: ASTM F1 233 Class III, ASTM 1915 Grade 3, HP White Level II-TP-0500.02 WMFL Level III

### CONSTRUCTION

This product is laminated polycarbonate and contains exposed polycarbonate surfaces with abrasion resistant coatings on both sides.

### INSTALLATION

All glazing should be installed in accordance with the guidelines set forth in the current edition of the Glass Association of North America (GANA) Glazing and Sealant Manuals. Glazing systems should incorporate a weep system to allow moisture and water to escape the glazing channel.

- Face Clearance: 1/8" per side
- Edge Clearance: 1/4"
- Bite Clearance: 1"

### MAINTENANCE

LEXGARD® is a laminated polycarbonate makeup which includes exposed polycarbonate (plastic) on both interior and exterior surfaces of the makeup. It is **very important** to follow maintenance and cleaning instructions closely. To ensure the polycarbonate is not damaged, only approved cleaners and cleaning methods should be used. For complete maintenance and cleaning instructions, please contact Insulgard Security Products.

The materials, products, and services of Insulgard™ Security Products, its subsidiaries and affiliates ("Seller") are sold subject to Seller's standard conditions of sale, which can be found at [www.polymershapes.com](http://www.polymershapes.com) and are available upon request. Although any information or recommendation contained herein is given in good faith, Seller makes no warranty or guarantee, express or implied, (i) that the results described herein will be obtained under end-use conditions, or (ii) as to the effectiveness or safety of any design incorporating seller's products, services or recommendations. Except as provided in Seller's standard conditions of sale, Seller shall not be responsible for any loss resulting from any use of its products or services described herein. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. No statement by Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right. ©2021 Polymershapes LLC. All rights reserved. Bulletblock™ and Insulgard™ are trademarks of Polymershapes LLC. Version: 6.13.25

**INSULGARD**  
**SECURITY PRODUCTS**  
[insulgard.com](http://insulgard.com) | 800.624.6315